



## Performance Specification Sheet

<b>Property</b>	<b>Typical Result</b>	<b>Test</b>	
Water Absorption	.75%	ASTM D 570	
Compressive Strength	52,625 psi	ASTM D 695	
Tensile Strength	28,675 psi	ASTM D 638	
Flexural Strength	41,650 psi	ASTM D 790	
Hardness	>85	ASTM D 785 (Rockwell)	
	55	ASTM D 2583 (Barber Coleman)	
Thermal Expansion	.35 x 10 <sup>-5</sup>	ASTM D 696	
Izod Impact	3.92	ASTM D 256	
Ball Impact	No Effect ½ lb. ball	NEMA LD 3-2000	
Bacteria & Fungus	Does not support growth	ASTM G 21 & 22	
Flammability	Class 1 & Class A	ASTM E 84-05	
	Flame Spread		10
	Smoke Development		85

The information contained in this technical data sheet is given by Klip BioTechnologies, LLC at no charge. It is based on technical data which Klip BioTechnologies believes to be reliable and is intended for use by persons having knowledge of this technical area at their own discretion and risk. Seller assumes no responsibility for the results obtained or damage incurred from the use of this technical data either in whole or in part by a buyer of EcoTop™ products.



Klip BioTechnologies, LLC – 7314 Canyon Rd. E. Puyallup, WA 98373